

LD2420D

Low Density Polyethylene Resin

Special Characteristics : InnoPlus LD2420D is produced by high pressure tubular process, a technology licensed by LyondellBasell. This grade offers easy processability, good balance of mechanical and optical properties. Film extruded from InnoPlus LD2420D has high tensile strength, elongation, good toughness and good tear strength.

Typical Applications : InnoPlus LD2420D is recommended for producing the heavy duty films, liners, shrink hoods and agricultural films.

Additives : No additives.

Typical Properties :

Properties	InnoPlus LD2420D	Units	Test Methods
<i>Physical Properties (Based on compression molded specimen)</i>			
Melt Flow Rate at 190 °C, 2.16 kg.	0.3	g/10 min	ISO 1133
Density	0.923	g/cm ³	ISO 1183
Melting Temperature	111	°C	ISO 11357
Vicat Softening Point	97	°C	ISO 306
Tensile strength at Yield	10	N/mm ²	ISO 527
Tensile Modulus	240	N/mm ²	ISO 527
<i>Film Properties* (Based on blown film)</i>			
Max. Tensile Strength (MD/TD)	24 / 18	MPa	ISO 527
Ultimate Elongation (MD/TD)	180 / 550	%	ISO 527
Dart Drop Impact	>150	g	ASTM D1709
Haze	<15	%	ASTM D1003
Gloss (20°)	>20	-	ASTM D2457
* film properties obtained from 70 microns film which was blown film extruded at blow up ratio 2.5			

Processing Condition :

Recommended melt temperature range from 170 °C to 220 °C.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Chemical makes no representations as to the accuracy or completeness of the information contained herein.